



**BODO MÖLLER
CHEMIE**

Your global partner for
mold making with **UREOL**®

Materials for modeling and mold making

Tooling boards and adhesives

With the Ureol® product line, we offer a variety of polyurethane and epoxy boards for tooling, modeling and mold making. In addition, we supply suitable adhesives for all Ureol® boards, which match in color, density, hardness, thermal expansion coefficient and glass transition point. The Ureol® product line convinces especially with constant high quality in addition to the excellent mechanical properties.

	Ureol® 80	Ureol® 250	Ureol® 450	Ureol® 600
Color	Off-white	Apricot	Apricot	Brown
Density (ISO 1183) kg/m³	80	250	450	620 - 680
Hardness Shore D (ISO 868)			40 - 50	45 - 55
Coefficient of thermal expansion (ISO 11359) 10 ⁻⁶ K ⁻¹			50 - 55	50 - 55
Deflection temperature, HDT (ISO 75) °C			80 - 85	70 - 75
Compressive strength (ISO 604) MPa	0.8	3.0	10 - 15	15 - 20
Flexural strength (ISO 178) MPa		4.5	10 - 15	15 - 20
Compressive modulus (ISO 604) MPa			400 - 500	
Abrasion (Taber) mm³/100U				
Dimensions (Length x Width) mm	2500 x 1200	2000 x 1000	1500 x 500	1500 x 500
Dimensions (Height) mm	100 200 300 400	100 200	50 75 100 150 200	50 75 100 150 200
Adhesives for EP boards				
Adhesives for PU boards	Ureol® ADH foam	Ureol® ADH foam	Ureol® ADH foam	Ureol® ADH 700 A/B



Ureol® 700	Ureol® 700 EP	Ureol® 750 EP	Ureol® 1000	Ureol® 1200	Ureol® 1200 orange	Ureol® 1600
Brown	Light blue	Light green	Beige	Green	Orange	Ivory
680 - 720	700 - 730	700 - 730	1000 - 1100	1200 - 1250	1200 - 1250	1600 - 1700
55 - 60	70 - 75	65 - 70	75 - 80	80 - 85	75 - 85	85 - 90
50 - 55	35 - 45	35 - 45	55 - 60	80 - 90	65 - 75	45 - 50
70 - 75	105 - 110	130 - 140	80 - 85	90 - 100	65 - 75	75 - 80
20 - 25	55 - 60	50 - 55	45 - 50	70 - 80	85 - 95	85 - 95
20 - 25	25 - 35	30 - 40	45 - 50	75 - 85	105 - 115	55 - 65
800 - 1000				1800 - 2300		5500 - 6500
					45 - 55	5500 - 6500
1500 x 500	1500 x 500	1500 x 500	1500 x 500	1000 x 500	1000 x 500	750 x 500
50	50	50	50	50	50	50
75	75	75	75	75	75	75
100	100	100	100	100	100	100
150	150	150				
200	200	200				
	Ureol® ADH EP 700 A	Ureol® ADH EP 750 A				
	Ureol® ADH EP 700/750 B	Ureol® ADH EP 700/750 B				
Ureol® ADH 700 A/B			Ureol® ADH 1000/1600 A	Ureol® ADH 1200 A	Ureol® ADH 1200 orange A	Ureol® ADH 1000/1600 A
			Ureol® ADH 1000/ 1200/1200or/1600 B	Ureol® ADH 1000/ 1200/1200or/1600 B	Ureol® ADH 1000/ 1200/1200or/1600 B	Ureol® ADH 1000/ 1200/1200or/1600 B

This content is protected by copyright. Graphics, texts, logos and pictures are only allowed to be copied, modified, published, transmitted or distributed after written approval by the BODO MÖLLER CHEMIE GmbH. Any product and company names may be registered trademarks or brands. Unauthorized use may result in claims for damages and injunctive relief cause. Industrial property rights of the manufacturer must be observed. All information about chemical and physical properties of our products as well as technical advice on their use, whether verbal or in writing and as the result of tests, are given to the best of our knowledge. However, this should only be considered as guidance, which is not guaranteed as correct and does not exonerate the customer from carrying out his own tests and trials in order to assess the practical suitability of the product for the purpose envisaged. The purchaser is solely responsible for the application, use and handling of the products and in doing so must observe all legal and official requirements as well as any rights of third parties. Apart from these, our general terms of delivery are applicable. Our range includes products, which under the classification of chemicals act, and regulations on hazardous substances, must be labelled according to their risk. The classification of these products is to be found in the relevant product data sheets or safety data sheets.

State 02/2026



■ GERMANY

Bodo Möller Chemie GmbH
Headquarters
Offenbach a. M.
+49 69 838326-0 | info@bm-chemie.de

■ AUSTRIA

Bodo Möller Chemie Austria GmbH
Vienna
+43 120 51907050 | info@bm-chemie.at

■ SWITZERLAND

Bodo Möller Chemie Schweiz AG
Winterthur
+41 52 2031930 | info@bm-chemie.ch

■ FRANCE

Bodo Möller Chemie France SAS
Sales Office *Ruaudin*
+33 243 240429 | bureau@bm-chemie.fr

Sales Office *Lyon*
+33 478 982337 | bureaulyon@bm-chemie.fr

■ BENELUX

Bodo Möller Chemie Benelux N.V.
Kruikebe (Belgium)
+32 3 2352135 | info@bm-chemie.be

■ SPAIN

Bodo Möller Chemie Spain s.l.
Rivas-Vaciamadrid
+34 916 286909 | info@bm-chemie.es

■ PORTUGAL

Bodo Moeller Chemie Portugal Unipessoal LDA
Valbom
+351 937 198020 | info@bm-chemie.pt

■ ITALY

Bodo Möller Chemie Schweiz AG
Succursale *Milano*
+41 799199904 | info@bm-chemie.ch

■ UNITED KINGDOM / IRELAND

Bodo Möller Chemie UK Ltd.
Manchester (Great Britain)
+44 161 8042029 | info@bm-chemie.co.uk

■ DENMARK

Bodo Möller Chemie Denmark Aps
Stenløse
+45 48 163470 | info@bm-chemie.dk

■ SWEDEN

Bodo Möller Chemie Sweden AB
Kållerød
+46 31 698952 | info@bm-chemie.se

■ NORWAY

Bodo Möller Chemie Norway NUF
Oslo
+45 48 16 34 70 | info@bm-chemie.no

■ FINLAND

Bodo Möller Chemie Finland Oy
Helsinki
+358 9 6829010 | info@bm-chemie.fi

■ POLAND

Bodo Möller Chemie Polska Sp. z o.o.
Suchy Las
+48 61 8220975 | info@bm-chemie.pl

Adhesive Competence Center & Laboratory
Poznań
+48 605 550427 | acc@bm-chemie.pl

■ ESTONIA / LATVIA / LITHUANIA

Bodo Möller Chemie Baltics OÜ
Tartu (Estonia)
+370 686 82 933 | info-baltics@bm-chemie.com

■ CZECH REPUBLIC / SLOVAKIA

Bodo Möller Chemie Czech & Slovakia, s.r.o.
Sales Office *Bratislava (Slovakia)*
+421 2 33006732 | info@bm-chemie.sk

Sales Office *Prague (Czech Republic)*
+420 239 045301 | info@bm-chemie.cz

■ HUNGARY

Bodo Möller Chemie Hungary Kft.
Tatabánya
+36 34 782019 | info@bm-chemie.hu

■ CROATIA

Bodo Möller Chemie Austria GmbH
Podružnica *Zagreb*
+385 91 2620276 | info-hr@bm-chemie.at

■ ROMANIA

Bodo Möller Chemie Austria GmbH
Sucursala *Bucuresti*
+40 314 362203 | info@bm-chemie.ro

■ TURKEY

Bodo Möller Turkey
Kimya Ürünleri Ticaret Ltd. Şti.
Beyoğlu/Istanbul
+90 212 2437634 | info-tr@bm-chemie.com

■ RUSSIA

Bodo Möller Chemie Russia LLC
Moscow
+7 495 1396000 | info@bm-chemie.ru

■ INDIA

Bodo Moeller Chemie India Pvt. Ltd.
Mumbai
+91 22 49741848 | info@bm-chemie.in

■ CHINA

Bodo Moeller Chemie (Shanghai) Co., Ltd.
Shanghai
+86 21 64750182 | info@bm-chemie.cn

Bodo Moeller Chemie Hong Kong Ltd.
Hong Kong
+86 21 64750182 | info@bm-chemie.hk

Sales offices in *Guangzhou, Shenzhen, Dongguan, Zhongshan, Chengdu, Chongqing, Kunshan, Zhengzhou*

■ THAILAND

Bodo Moeller Chemie (Thailand) Co., Ltd.
Sales Office *Bangkok*
+66 98 269 6088 | info-th@bm-chemie.com

■ VIETNAM

Bodo Moeller Chemie Vietnam Co., LTD
Hanoi
+84 9 63 69 45 65 | info-vn@bm-chemie.com

■ JAPAN

Bodo Moeller Chemie Japan K.K.
Tokyo
+81 3 4563 9908 | info-jp@bm-chemie.com

■ SOUTH KOREA

Bodo Möller Chemie Korea LTD.
Seoul
+82-10-6388-8272 | info-kr@bm-chemie.com

■ ISRAEL

BM Chemie Israel Ltd.
Tel Aviv-Yafo
+972 36 377366 | info@bm-chemie.co.il

■ MIDDLE EAST

Bodo Möller Chemie Middle East FZE
Dubai (UAE)
+971 4 8813833 | info@bm-chemie.ae

■ EGYPT

Bodo Moeller Chemie Egypt SAE
Bodo Moeller Chemie Egypt Import Ltd.
Sales Office *Cairo*
+20 2 226963-91 | info@bm-chemie.com.eg

Bodo Moeller Chemie Egypt SAE
Sales Office *Alexandria*
+20 3 3922061 | info@bm-chemie.com.eg

Production Plant Sadat City
+20 4 82656041 | info@bm-chemie.com.eg

■ MOROCCO

Bodo Moeller Chemie Morocco SARLAW
Casablanca
+212 522 262732 | info@bm-chemie.ma

■ KENYA

Bodo Moeller Chemie Kenya Ltd.
Nairobi
+254 788 071608 | info@bm-chemie.co.za

■ NIGERIA

Bodo Moeller Chemie Nigeria FZE
Lekki Free Zone, Lagos
+971 4 8813833 | info@bm-chemie.ae

■ SOUTH AFRICA / SUB-SAHARA REGION

Bodo Möller Chemie South Africa (PTY) Ltd.
Sales Office *Port Elizabeth*
+27 41 3641335 | info@bm-chemie.co.za

Sales Office *Johannesburg*
+27 114 501745 | info@bm-chemie.co.za

■ USA

Bodo Moeller Chemie Corp.
Atlanta, Georgia
+1 770 2952288 | info-us@bm-chemie.com

■ MEXICO

Bodo Möller Chemie México, S. de R.L. de C.V.
Puebla
+52 222 2405168 | info@bm-chemie.mx

BCC
A company of BODO MÖLLER CHEMIE
Chihuahua
+52 614 421 0287 | serviciocliente@dqnte.com